

Mastertop[®]538

Industrial grade self-levelling cementitious floor overlay

Description

Mastertop[®]538 is a self-smoothing, cementitious, non-structural, floor overlay for re-levelling and refurbishing cementitious based floor slabs. Mastertop[®]538 can be laid at thicknesses from 4mm when hand applied or 6mm when pump applied, maximum 10mm. Mastertop[®]538 simply requires coating with a resin based seal coat.

Recommended for

- Finishing rough undulating floors
- Leveling up floors
- Refurbishing old floors
- Fastrack industrial refurbishment

Features and benefits

- Highly fluid and pumpable for fast installation
- Rapid strength gain
- Ready for foot traffic after 3-4 hours
- Return to service in 24 hours
- Rapid cure
- Self-smoothing
- Good compressive strength

Packaging

Mastertop[®]538 is available in 25kg bags.

Performance data (typical)*

	1 day	28 days
Compressive strength (AS 2073)	>12N/m ²	>35N/m ²
Flexural strength	>2N/mm ²	>4N/mm ²
Tensile strength (28 days)	>2N/mm ²	
Work time @ 23°C	30 mins	
Setting times @ 23°C – Initial	1½ - 2hours	
– Final	2 – 3 hours	
Foot traffic @ 23°C 50%RH	approx. 3 hours	
Drying shrinkage @ 7 days (BASF CC SA.Test Method)	<300 microstrain	
Pull off bond strength	1.0MPa	

*Properties listed are only for guidance and are not a guarantee of performance

Application directions

Substrate condition

Substrate must be clean and free of oil, sealers, curing compounds, paint, polymer coatings, dust or other foreign (contaminating) matter.

Remove all weak or broken pieces of concrete. If necessary, employ mechanical cleaning methods and equipment. If sealers, paint, polymer coatings or curing compounds are present on concrete substrate, remove with mechanical shot blasting or surface grinding equipment.

Mastertop[®]538 is best applied where the application temperature is between 5°C and 35°C. Outside this range, please refer to your local BASF Construction Chemicals SA Technical Representative.

Mastertop[®]538

Voids and cracks (water pipes, holes, drainage pipes etc) should be filled to prevent seepage through to lower levels. Consult with your local BASF Construction Chemicals SA Technical Representative for product recommendations. Note: Joints should always be cut in toppings directly above those in the base slab to avoid random cracking.

Priming

Apply Rheomix 111 diluted 50 / 50 with potable water to the dry substrate by roller, brush, low pressure spray or squeegee at a rate of approximately 5m² / Litre. On very porous or absorbent substrates, 2 coats may be required to effectively seal the substrate. Take care to avoid ponding of the primer. Allow to dry fully before application of Mastertop[®]538.

Mixing

Mechanical mixing is required for Mastertop[®]538. For small areas, a slow speed stirrer of not more than 600 rpm, fitted with a helical paddle is suitable. Mixing time is 3 minutes.

Place the required quantity of water into the mixing vessel. Whilst mixing, slowly add the powder to the water within 2 minutes then mix for a further 1 minute. Allow mixed Mastertop[®]538 to stand for 3 minutes and then remix prior to application. Use chilled water at high temperatures for longer application time. For improved efficiency and continuous production of Mastertop[®]538, it is recommended to use at least two mixing buckets.

For larger jobs, the use of a mechanical mixer / pump unit is recommended. Refer to your local BASF Construction Chemicals SA Technical Representative for suitable machines.

Method of use

Pour mixture over substrate or pump through a suitable pump to desired thickness. Use a gauging /pin rake to control thickness.

Whether pouring from a mixing vessel or using a mechanical mixer with an application hose, the discharge point should be approximately 200mm from the floor to prevent splashing and air entrapment.

Progress should be steady and even. Application should take place continuously into the preceding wet material to ensure even thickness and flow. Do not make new edges and 'fill in' the middle.

The fresh wet topping can be rolled immediately with a suitable long spiked roller to release all air retained within the underlayment. Do not roll material that has been applied for more than 2-3 minutes.

Curing

Mastertop[®]538 is self-curing, but as with all cementitious products in hot weather, take adequate measures to protect it from exposure to direct sunlight and hot winds. Do not use water spray or liquid membrane curing compounds as these may affect the surface texture or prevent bonding of subsequent adhesives used with floor coverings.

Coverage

A 25kg bag of Mastertop[®]538 mixed with 4.0-4.25 litres of water yields 13 litres.



The Chemical Company

Mastertop[®]538

Cleaning

Tools should be cleaned with water before the material hardens. Hardened material will need to be mechanically removed.

Shelf life

Mastertop[®]538 can be stored in tightly sealed original bags for 6 months if kept dry and at a moderate temperature.

Precautions

Mastertop[®]538 is not toxic, but as with other products containing cement it has an alkaline nature and thus can be irritating to skin and eyes. Wear simple dust masks and gloves when handling. Keep out of reach of children. Wash off splashes of material with clean water. If irritation persists, seek medical advice. Refer to Material Safety Data Sheet for further information.

Storage

Store under cover, out of direct sunlight and protect from extremes of temperatures.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF Construction Chemicals SA's Technical Services Department.

Safety precautions

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs (which can also be tainted with vapour until product fully cured or dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use.

Note

For professional use only

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF Construction Chemicals SA representative. BASF Construction Chemicals SA reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

All products originating from BASF Construction Chemicals' SA facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001:2000.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control.

As all BASF's technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

BASF Construction Chemicals South Africa (Pty) Ltd

852 Sixteenth Road, Midrand
PO Box 2803, Halfway House, 1685
Tel: +27 11 203 2405
Fax: +27 11 203 2679
website : www.basf-cc.co.za

11 Pullinger Street, Westonaria, 1779
P.O. Box 420, Westonaria, 1780
Tel: +27 11 754 1343
Fax: +27 11 754 1105

Revised : January 2010